



DATA SHEET DIGITAL PRINTING VINYL REMOVABLE ADHESIVE CSE25

Semi-rigid 200 micron PVC film, coated with a pressure sensitive acrylic adhesive. Suitable for solvent inkjet printers. Matt surface finish.

SPECIFICATIONS:

	<u>Average values</u>	<u>Standard</u>
• Thickness (µm):	200	
• Total caliper (µm):	350	
• Total specific weight (g/m ²):	445	HEXGSM001
• Tensile strength (N/25mm):	>100	HEXNFX41021
• Elongation at break (%):	NA	HEXNFX41021
• Dimensional stability (mm): after 168h at 70°C	< 0.4	HEXRET001

PRINTER AND INK COMPATIBILITY:

- Solvent inkjet printers.

LINER:

- Unprinted silicone coated paper liner 137 g/m².
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

- | | | |
|-----------------------------------|----|-----------|
| • Peel on glass at 180° (N/25mm): | | HEXFTM001 |
| 20 minutes after application | 1 | |
| 24 hours after application | 2 | |
| • Initial tack (N/25mm): | 4 | HEXFTM009 |
| • Release (N/25mm): | NC | HEXFTM003 |
- The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).

RECOMMENDATIONS:

- Leave a 2 cm (3/4in) unprinted border around the printed area.
- Touch dry after less than 10 minutes depending on printer used.
- Optimum drying time before laminating or varnishing is 24 hours.
- Minimum application temperature +15°C (+59°F).
- Optimum environment -10°C to +40°C (14°F to +104°F).
- Solventbased acrylic adhesive.
- Immediate and removable adhesion.
- Very good adhesion on glass.
- Indoor application.
- If applied on monomeric or polymeric plasticised vinyl films a removable adhesive may become semi-permanent. The duration of the application and the type of exposure may accelerate the phenomenon.

SHELF LIFE:

- 1 year at +15°C...+25°C (+59°F...+77°F) and 50% relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

DURABILITY: (on flat surface)

- Unprinted vertical exposure: 6 months without important adhesive residue.
- Printed vertical exposure: 3 months without important adhesive residue.

Note:

If in doubt about the compatibility of the product with any particular application we recommend that the user carry out a trial before the final application or seek advice from the manufacturer. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force. All data are believed to be correct but do not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The buyer has to determine the suitability of the materials for the intended purpose prior to purchase. HEXIS S.A. or its affiliates assume no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: www.hexisgroup.com.