



DATA SHEET DIGITAL PRINTING

FLEXPRINT3

Self-adhesive 160µm PVC film for cutting plotters and hot transfer of markings and logos onto fabrics (cotton, polyester and similar fibres). Gloss finish.

SPECIFICATIONS:

Average values

- Thickness film + adhesive (µm):

160

PRINTER AND INK COMPATIBILITY:

- Compatible with solvent or eco-solvent inkjet printers.

RECOMMENDATIONS:

- Print, leave to dry for 12 hours at least and cut a positive image.
- Transfer with a HEX600 or HEX700 transfer film.
- Pre-heat the press and the fabric before application.
- Press at 155°C (311°F) for 15 seconds.
- The HEX600 or HEX700 may be removed while hot.
- After transfer, wait for 24 hours at least before washing.
- Wash at 40°C (104°F) max., a trial is recommended.
- Iron the T-shirt inside out.
- For further information on application methods of FLEXPRINT3, refer to the technical bulletin DIGITAL MEDIA FOR FABRICS on the professionals pages of the web site www.hexisgroup.com.

SHELF LIFE:

- 1 year at +15°C...+25°C (+59°F...+77°F) and 50% relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

Note:

If in doubt about the compatibility of the product with any particular application we recommend that the user carry out a trial before the final application or seek advice from the manufacturer. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force. All data are believed to be correct but do not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The buyer has to determine the suitability of the materials for the intended purpose prior to purchase. HEXIS S.A. or its affiliates assume no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: www.hexisgroup.com.