



## DATA SHEET DIGITAL PRINTING OPAQUE POLYESTER POPNC400

Semi-rigid 420 micron PVC film for inkjet printing with solvent inks, for display applications.

### **SPECIFICATIONS:**

	<u>Average values</u>	<u>Standard</u>
• Total caliper (µm):	420	
• Total specific weight (g/m <sup>2</sup> ):	645	HEXGSM001
• Opacity (%):	> 99	HEXOPA001

### **PRINTER AND INK COMPATIBILITY:**

- Solvent inkjet printers.

### **RECOMMENDATIONS:**

- Touch dry after less than 15 minutes depending on printer used.
- Before laminating, inks need to dry for 24 hours.
- Application temperature +10°C...+30°C (+50°F...+86°F) at 30...70% relative humidity.
- Media and prints are affected by direct projections of liquids and finger prints (gloves strongly recommended).

### **SHELF LIFE:**

- 1 year at +15°C...+25°C (+59°F...+77°F) and 50% relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

#### **Note:**

Because of the great variety of substrates and possible application methods the installer must examine the suitability of the media for each application.

The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force.

All published data are based on measurements carried out regularly under laboratory conditions. They do, however, not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The seller assumes no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: [www.hexisgroup.com](http://www.hexisgroup.com).