



DATA SHEET DIGITAL PRINTING PHOTO PAPER

PPH 190 AD

195 micron photo paper, coated with permanent acrylic pressure sensitive adhesive, suitable for aqueous inks. Gloss or satin surface finish.

SPECIFICATIONS:

	<u>Average values</u>	<u>Standard</u>
• Total caliper (μm):	305	
• Specific weight (g/m^2):	300	HEXGSM001
• Adhesive paper weight (g/m^2):	220	HEXGSM001

PRINTER AND INK COMPATIBILITY:

- Aqueous dye inks.
- Thermal printers.

LINER:

- Silicone liner paper 80 g/m^2 grey HEXIS print.

ADHESIVE PROPERTIES:

• Peel on glass at 180° (N/25mm):		HEXFTM001
20 minutes after application	32	
24 hours after application	35	
• Initial tack (N/25mm):	11	HEXFTM009
• Release (N/25mm):	0.2	HEXFTM003
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

RECOMMENDATIONS:

- Touch dry after less than 5 minutes depending on printer used.
- The dye inks are sensitive to light, these prints should not be exposed to direct sun light.
- The print may be cold laminated with a clear self-adhesive vinyl (Hexis V700). **NOT SUITABLE FOR HOT LAMINATING OR ENCAPSULATING.**
- The visual appearance of the print may be modified/improved/protected by a judicious choice of a gloss, matt or satin lamination (V700).
- Before laminating or coating, inks need to dry for 24 hours.
- Media and prints are affected by direct projections of liquids and finger prints (gloves strongly recommended).
- Application temperature +10°C...+30°C (+55°F...+86°F) at 30...70% relative humidity.
- Adhesion is immediate and permanent (not re-positionable).
- Very good adhesion on glass, steel, aluminium, PVC, melamine, ... except grained surfaces or acrylic paints.

SHELF LIFE:

- 1 year at +15°C...+25°C (+59°F...+77°F) and 50% relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

Note:

If in doubt about the compatibility of the product with any particular application we recommend that the user carry out a trial before the final application or seek advice from the manufacturer. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force. All data are believed to be correct but do not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The buyer has to determine the suitability of the materials for the intended purpose prior to purchase. HEXIS S.A. or its affiliates assume no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: www.hexisgroup.com.