



## DATA SHEET DIGITAL PRINTING VINYL - REMOVABLE ADHESIVE V211WGI

Polymeric calendered cadmium-free 70 micron PVC film, coated with a removable pressure sensitive acrylic adhesive. Suitable for solvent inkjet printers. Gloss surface finish.

### **SPECIFICATIONS:**

	<u>Average values</u>	<u>Standard</u>
• Thickness (µm):	70	
• Total caliper (µm):	260	
• Total specific weight (g/m <sup>2</sup> ):	280	HEXGSM001
• Tensile strength (N/25mm):	min. 35	HEXNFX41021
• Elongation at break (%):	min. 100	HEXNFX41021
• Dimensional stability (mm): after 168h at 70°C	< 0.3	HEXRET001

### **PRINTER AND INK COMPATIBILITY:**

- Solvent inkjet printers.

### **LINER:**

- Silicone PE paper 145 g/m<sup>2</sup> grey HEXIS print.
- Stable under hygrometric variations.

### **ADHESIVE PROPERTIES:**

• Peel on glass at 180° (N/25mm): 20 minutes after application	7	HEXFTM001
24 hours after application	9	
• Initial tack (N/25mm):	4	HEXFTM009
• Release (N/25mm):	0.20	HEXFTM003
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

**RECOMMENDATIONS:**

- Touch dry after less than 10 minutes depending on printer used.
- The surface aspect can be advantageously improved by applying the appropriate laminate (type PC30G2 or V750).
- The optimum drying time before laminating or varnishing is 24 hours.
- Minimum application temperature +10°C (+50°F).
- Optimum environment -20°C to +60°C (-4°F to +140°F).
- Removable solvent based acrylic adhesive.
- Immediate adhesion, removable.
- Very good adhesion on glass, steel, aluminium, PVC, melamine, ... except grained surfaces or acrylic paints.
- If applied on monomeric or polymeric plasticised vinyl films a removable adhesive may become semi-permanent. The duration of the application and the type of exposure may accelerate the phenomenon.
- In the case of painted substrates self-adhesive media must only be applied onto the undamaged original paintwork. If the paint is not the original paintwork and/or if it is damaged, the application and the removal are at the installer's risk.

**SHELF LIFE:**

- 1 year at +15°C...+25°C (+59°F...+77°F) and 30 to 70% relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

**DURABILITY:** (on flat surface)

- Unprinted vertical outdoor exposure: 6 months without important adhesive residue.
- Printed and laminated vertical outdoor exposure: 12 months (if edges are sealed by a liquid laminate).
- Printed vertical outdoor exposure: 3 months without important adhesive residue.

**Note:**

Because of the great variety of substrates and possible application methods the installer must examine the suitability of the media for each application. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force.

All published data are based on measurements carried out regularly under laboratory conditions. They do, however, not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The seller assumes no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: [www.hexisgroup.com](http://www.hexisgroup.com).