



DATA SHEET DIGITAL PRINTING VINYL PERMANENT ADHESIVE V3000WG

Monomeric calandered cadmium-free 100 micron PVC film, coated with a grey pressure sensitive acrylic adhesive. Suitable for solvent, eco-solvent inkjet printers. Gloss surface finish.

SPECIFICATIONS:

	<u>Average values</u>	<u>Standard</u>
• Thickness (µm):	100	
• Total caliper (µm):	255	
• Total specific weight (g/m ²):	300	HEXGSM001
• Tensile strength (N/25mm):	min. 40	HEXNFX41021
• Elongation at break (%):	min 100	HEXNFX41021
• Dimensional stability (mm): after 168h at 70°C	< 0.8	HEXRET001

PRINTER AND INK COMPATIBILITY:

- Solvent, eco-solvent inkjet printers.

LINER:

- Siliconed kraft paper 135 g/m² with light blue HEXIS print.
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

• Peel on glass at 180° (N/25mm):		HEXFTM001
20 minutes after application	15	
24 hours after application	20	
• Initial tack (N/25mm):	10	HEXFTM009
• Release (N/25mm):	0.2	HEXFTM003
• The adhesive is resistant to most chemicals (alcohol, diluted acids, oils).		

RECOMMENDATIONS:

- Touch dry after less than 10 minutes depending on printer used.
- The surface aspect can be advantageously improved by applying the appropriate matt, satin or gloss laminate (type V700).
- Optimum drying time before laminating or varnishing is 24 hours.
- Minimum application temperature +10°C (+50°F).
- Optimum environment -40°C to +90°C (-40°F to +194°F).
- Grey solventbased acrylic adhesive.
- Immediate and permanent adhesion.
- Very good adhesion on glass, steel, aluminium, PVC, melamine, ... except grained surfaces or acrylic paints.
- Do not leave the media in the printer outside printing sessions. Extended contact (over 6 hours) without moving may ripple the media during the cooling down process.

SHELF LIFE:

- 1 year at +15°C...+25°C (+59°F...+77°F) and 50% relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

DURABILITY: (on flat surface)

- Unprinted vertical outdoor exposure: 4 years.
- Printed and laminated vertical outdoor exposure: 3 years.
- Printed vertical outdoor exposure: 2 years.

Note:

If in doubt about the compatibility of the product with any particular application we recommend that the user carry out a trial before the final application or seek advice from the manufacturer. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force. All data are believed to be correct but do not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The buyer has to determine the suitability of the materials for the intended purpose prior to purchase. HEXIS S.A. or its affiliates assume no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: www.hexisgroup.com.