



DATA SHEET ERASBALE WHITEBOARD SHORT TERM DRY WIPE - DW829B – DW899B....

110 micron PVC film, coated with a pressure sensitive acrylic adhesive. Dry wipe surface for use with erasable marker pens. Indoor applications.

SPECIFICATIONS:

	<u>Average values</u>	<u>Standard</u>
• Thickness (µm):	110	
• Specific weight (g/m ²):	165	HEXGSM001
• Dimensional stability (mm): 168 hours at 70°C	< 0.4	HEXRET001

LINER:

- Silicone coated paper liner 137 g/m² with blue HEXIS print.
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

• 180° peel on glass (N/25mm): after 20 minutes	15	HEXFTM001
after 24 hours	20	
• Initial tack (N/25mm):	12	HEXFTM009
• Release (N/25mm):	0.20	HEXFTM003

RECOMMENDATIONS:

- Minimum application temperature: +15°C (+59°F).
- Temperature range: +15°C to +30°C (+59°F to +86°F).
- For use with dry erasable pens **BIC VELLEDA**® Ref. 1711/1791/1781.
- Markings not older than one week are easily wiped off with a dry cloth.
- Easily cleaned with window cleaning liquid.
- Indoor usage only, not resistant to UV-rays.
- In the case of painted substrates self-adhesive media must only be applied onto the undamaged original paintwork. If the paint is not the original paintwork and/or if it is damaged, the application and the removal are at the installer's risk.

SHELF LIFE:

- Shelf life before application: 1 year at +15°C... +25°C (+59°F... +77°F) and 30% to 70% relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

DURABILITY:

- Unmarked vertical indoor application: 2 years.

Note:

Because of the great variety of substrates and possible application methods the installer must examine the suitability of the media for each application. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force.

All published data are based on measurements carried out regularly under laboratory conditions. They do, however, not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The seller assumes no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: www.hexisgroup.com.