



## SUPTAC HEX'PRESS DATA SHEET HX5000

Cadmium-free polymeric calendered PVC film 65  $\mu\text{m}$ , carrying a pressure sensitive acrylic adhesive. Structured adhesive for convenient application and elimination of air bubbles.

### **SPECIFICATIONS:**

	<u>Average values</u>	<u>Standard</u>
• Thickness ( $\mu\text{m}$ ):	65	
• Tensile strength (N/25mm):	min. 35	HEXNFX41021
• Elongation at break (%):	min. 100	HEXNFX41021
• Dimensional stability (mm):	< 0.4	HEXRET001

### **LINER:**

- Embossed silicone PE paper 145 g/m<sup>2</sup> with light grey HEXIS print.
- Stable under hygrometric variations.

### **ADHESIVE PROPERTIES:**

• 180° peel on glass (N/25mm):		HEXFTM001
after 20 minutes	13	
after 24 hours	16	
• Initial tack (N/25mm):	14	HEXFTM009
• Release (N/25mm):	0.20	HEXFTM003
• Resistant to most oils, diluted acids, alcohol and hydrocarbons.		

**RECOMMENDATIONS:**

- Minimum application temperature: +10°C (+50°F)
- Temperature range: -40°C to +90°C (-40°F to +194°F)
- The rolls must be stored in the same environment as the cutting machine.
- If the pressure of the knife is too high, the silicone liner may get slit and absorb some of the adhesive and thus make weeding more difficult or even delaminate the liner in the weakened areas. In all cases it is preferable to weed immediately after cutting.
- In order to make transfer easier HEXIS offer a complete range of accessories including different types of squeegees (plastic or felt; hard, medium or soft).
- If applying on glass the target surface must be cleaned right up to the edges. With the transfer tape still in place the complete surface of the graphics should be pressed down in wiping sweeps.
- The minimum application temperature must be complied with both for ambient environment and the substrate. Hygrometrics have no influence except in the case of dry application.
- In a cold environment the application tape should be left longer before removal and several days are required before the vinyl reaches the final adhesion.
- On a cold substrate condensation may occur between the substrate and the film, it is recommended to pre-heat the substrate.
- The HX5000 can only be dry applied because of its special HEX'PRESS liner. The structured adhesive makes the film repositionable during transfer, however the film still needs to be firmly applied to achieve optimum adhesion of the HX5000 on the substrate. In particular press the squeegee firmly down along the contours of the graphic.
- Firmly apply the squeegee on the contours.
- A seaming varnish may be applied.
- In the case of painted substrates self-adhesive media must only be applied onto the undamaged original paintwork. If the paint is not the original paintwork and/or if it is damaged, the application and the removal are at the installer's risk.

**ADHESIVE:**

- Acrylic solvent based.
- Immediate and permanent adhesion.
- Structured adhesive for convenient application and elimination of air bubbles.

**SHELF LIFE:**

- 2 years at +15°C... +25°C (+59°F... +77°F) and 30% to 70% relative humidity, rolls standing upright in a dustfree environment before usage and in the original packing.

**DURABILITY:**

The pigments in the vinyl influence the stability of the colours. The durability is confirmed by aging tests of HX5000 polymeric films under UV-rays and under natural exposure; the durations indicated below are those found when a reduction or a gradual modification of the appearance is noticeable.

Colour	Nordic climate Central Europe	Mediterranean climate	Tropical and marine climate	Desert climate
White. Black gloss	10 years	8 years	7 years	6 years
Others colours	8 years	6 years	5 years	4 years
Except yellows / reds	6 years	5 years	4 years	3 years

These results are obtained under vertical exposure outdoors and the conditions of the indicated durability depend on this position up to a few degrees. Other positions increase the climatic influences and alterations of gloss, colour and may even cause a slight powder effect to appear in outdoor conditions.

**Note:**

Because of the great variety of substrates and possible application methods the installer must examine the suitability of the media for each application. The methods of measuring for the standards quoted above are the basis for the development of our own measuring methods which are available on request (partial application). You are invited to enquire for the latest instructions in force.

All published data are based on measurements carried out regularly under laboratory conditions. They do, however, not constitute a warranty, representation or promise, express or implied as to the condition, quality, merchantability, fitness for a product, or that such product will satisfy any requirement for a specific property or capacity or special methods, all such warranties being hereby expressly disclaimed. The seller assumes no liability for claims beyond the replacement value of any product proven to be defective in material or workmanship and is in no way liable for direct, indirect, special, incidental damages or consequential loss including without limitation lost profits or loss of use, whether based on contract, tort or any other legal theory. Product specifications may change without prior notice. Our website is automatically updated: [www.hexisgroup.com](http://www.hexisgroup.com).